intertek Total Quality. Assured.

## Report Number :

DELC21002442





**TEST REPORT** 

ULR - TC-566321221002442P

NUMBER : DELC21002442 DATE : 28-Feb-2021

APPLICANT : **Shakti Overseas** 2762, 1st Floor, Qutab Road, Sadar Bazar, Delhi, Delhi, 110006, India ATTN : **Nitin Sachdeva** 

: THE SUBMITTED SAMPLE SAID TO BE HOOK AND EYES. Sample Description **TESTED COMPONENTS:-**[1] SILVER METAL HOOK [2] SILVER METAL PLATE [3] SILVER METAL BAR [4] SILVER METAL HOOK (INNER PLATE) Date Received/date Test Started : 25 Feb 2021 **Date Confirmation Received** 25 Feb 2021 • Buyer NOT PROVIDED P.O.No Fiber Content Style ADJUSTABLE • Color NOT PROVIDED • Article No 1

# TEST CONDUCTED : AS PER THE REQUEST OF THE APPLICANT. FOR FURTHER DETAILS PLEASE REFER TO ENCLOSED PAGE(S)

AUTHORIZED BY FOR Intertek India Private Limited [Analytical - Gurgaon]

RAVINDRA S LAB MANAGER - C&A

TEX/59



**TEST REPORT** 

ULR - TC-566321221002442P NUMBER : DELC21002442 DATE : 28-Feb-2021

#### **CONCLUSION**:

**Corrosion Resistance** 

Μ

NOTE:M = MEETS REQUIREMENT,\* = REQUIREMENT NOT PROVIDED,# = EXEMPTED,# = EXEMPTED,SC = SEE COMMENT## = NOT PERFORMEDNR = NOT REQUESTEDNR = NOT REQUESTEDC = CONFIRM LABEL



#### TEST REPORT

ULR - TC-566321221002442P NUMBER : DELC21002442 DATE : 28-Feb-2021

TEST CONDUCTED (AS REQUESTED BY THE APPLICANT)

#### 1. Corrosion Resistance

- ISO 9227

**TESTED CONDITION:** 

(1) SODIUM CHLORIDE (NaCI) SOLUTION CONCENTRATION = 50 gm/L

(2) PH = 6.8,

(3) CHAMBER TEMPERATURE (°C) = 35°C

(4) EXPOSURE PERIOD = 24 Hours.

[1]

Grade: 10 (No Visual Defect Observed on Sample)	<u>Requirement</u> No Corrosion
[2]	
Grade: 10 (No Visual Defect Observed on Sample) [3]	<u>Requirement</u> No Corrosion
Grade: 10 (No Visual Defect Observed on Sample) [4]	<u>Requirement</u> No Corrosion
Grade: 10 (No Visual Defect Observed on Sample)	Requirement No Corrosion

### ## END OF THE TEST REPORT ##

This report is made solely on the basis of your instructions and/or information and materials supplied by you. It is not intended to be a recommendation for any particular course of action. Intertek does not accept a duty of care or any other responsibility to any person other than the Addressee in respect of this report and only accepts liability to the Addressee insofar as is expressly contained in the terms and conditions governing Intertek's provision of services to you. Intertek makes no warranties or representations either express or implied with respect to this report save as provided for in those terms and conditions. We have aimed to conduct the Review on a diligent and careful basis and we do not accept any liability to you for any loss arising out of or in connection with this report, in contract, tort, by statute.

http://www.intertek.com/terms.